



Heritability of Fiber Strength in Genetically Engineered Cotton

O.L. May¹, T.J. Wofford², and M. E. John³

¹USDA-ARS, Florence; ²Monsanto, St. Louis, MO; ³Monsanto Agracetus Campus, Madison, WI.

ABSTRACT

Fiber strength must be increased for cotton to remain competitive as a textile fiber. The findings of a 2-yr study of cotton genetically engineered to express increased fiber strength are reported. Particle bombardment transformation of 'Deltapine 50' was accomplished by Monsanto. In field trials, fiber strength was increased by 25-75% over the non-transformed Deltapine 50. However, inconsistent expression of strength may prevent commercialization of cotton germplasm derived from this transformation. These data may have general implications for transgenic breeding in that transformation events imparting inconsistent expression of the value added trait should be discarded early in the breeding process.

Introduction

Global competition in yarn and textile manufacture in the 1990s has engendered the switch from ring spinning to more productive open-end yarn manufacture. Modernization of spinning and textile manufacturing technologies necessitate fiber property improvement, particularly fiber strength, for the new technology to function efficiently. Open-end spun yarns have lower strength than similar size ring spun yarn (Deussen, 1992), but this reduced yarn strength can be ameliorated through better fiber strength.

Improving fiber strength by conventional breeding has been successful (May, 1998), but biotechnology coupled with breeding offers the possibility of more immediate improvement. Monsanto Company is a major player in incorporating value-added traits in cotton cultivars. 'Deltapine 50' (DP 50) plants with increased fiber strength were found after transformation by particle bombardment. Unusual segregation for fiber strength and GUS were noted in some small R₃ and R₄ populations descendent from the original R₀ plant. The objective of this study was to determine the heritability and expression of fiber strength under field conditions by examination of large numbers of parent-offspring relationships.

Materials and Methods

As a result of Monsanto's discovery program, DP 50 plants with increased fiber strength (about 25%) were discovered in the R₂, R₃, and R₄ generations after a single transformation event. Transformation was accomplished by particle bombardment of meristems (McCabe and Martinell, 1993), using the Monsanto proprietary ACCELL technology. The inserted plasmid contained a GUS (B-glucuronidase) marker gene (Jefferson *et al.*, 1987) and a proprietary gene driven by a fiber specific promoter. Unusual segregation for fiber strength was noted in the R₃ and R₄ generations (M.E. John, unpublished data),

inconsistent with a single dominant gene genetic model for the GUS and proprietary gene loci. These data prompted further studies with increased population size and numerous parent-offspring relationships to assess heritability of fiber strength.

Populations derived from seed of three R₃ greenhouse plants derived from one transformation event (plants and derived populations designated M₁₆, M₁₇, and M₁₈) that expressed elevated fiber strength were evaluated in 1996, 1997, and 1998 at the Pee Dee Research and Education Centre, Florence, SC with DP 50 as the control. Seeds were planted at 0.3 m spacing into soil prepared for cotton production according to Clemson University Co-operative Extension Service recommendations (Lege *et al.*, 1996). Plants in the M₁₆, M₁₇, and M₁₈ populations were assayed for GUS expression prior to anthesis using techniques in which leaf tissue samples from every plant were placed in tissue culture plates and 0.5 ml of GUS-buffered substrate was added. Plates were incubated overnight and tissue samples were rated for appearance of blue colour. Evidence of blue staining was taken to indicate GUS activity (McCabe and Martinell, 1993). Most leaf tissue assays were confirmed through GUS assays of pollen but some plants produced no pollen so there leaf assays could not be confirmed.

Seed from 1996 plants were planted in 1997 as progeny rows. Some plants in 1996 had difficulty setting seed so rows contained as few as two plants to as many as about 700 plants. In total, about 10,000 plants were evaluated in 1997. GUS assays were conducted as in 1996, except that most assays were in the field, using a simplified technique of McCabe and Martinell (1993). Microcentrifuge tubes were filled with 0.5 ml of GUS-buffered substrate and clipped to the plant, in the process immersing a piece of leaf tissue in the buffer. Tubes were allowed to incubate overnight at ambient temperatures and then read for presence of blue staining. Duplicate runs in tissue culture plates incubated at 37° C in the laboratory and

with microcentrifuge tubes in the field on several progeny rows produced identical results (May, unpublished data); confirming the reliability of the simplified GUS assay.

Results and Discussion

Fiber strength of GUS + R₄ plants was increased from 25% to nearly 75% over the DP 50 controls (Table 1), further illustrating the more immediate crop improvement possible with biotechnology. Unfortunately, wide segregation for fiber strength was noted among GUS+ plants within the M₁₆ population (due to space limitations, only findings from the M₁₆ cotton population are discussed), indicating lack of fit of fiber strength segregation to a simple genetic model. GUS+ plants ranged in fiber strength from about 15 g/tex to as much as 30 g/tex (DP 50 average T₁=17.1 ±1.1 g/tex; Table 1). We have no explanation for the segregation in fiber strength among the GUS+ plants. Southern and Northern blot analysis might have indicated if the proprietary gene was present and functioning in all GUS+ plants, but such analyses were not available. We found three GUS- plants in the M₁₆ population. The origin of the GUS- plants is unclear, as the R₃ plant with elevated fiber strength from which M₁₆ was derived was putatively a GUS homozygote (based on GUS expression in pollen; M.E. John, unpub. data). The three GUS- plants could reflect an inadvertent seed mixture, gene elimination, silencing, or some other cryptic molecular event.

Based on these unusual segregation data, our goal was then to further observe segregation for GUS and fiber strength among progeny (particularly GUS+ homozygotes) derived from selfing M₁₆ plants, and those we derived from outcrossing GUS+ plants to various cultivars. The R₅ progeny of 1996 M₁₆ plants exhibited wide segregation for fiber strength (Table 1), similar to what we observed in the R₄ generation. For example, M₁₆ plant #1 was a high strength R₄ plant, and an apparent GUS+ homozygote, that produced 15 GUS+ progeny that segregated into a wide range (17.9-27.1 g/tex) of fiber strength. Other GUS+ apparent homozygotes such as plants 6, 11, 12, 21, 41, and 44 similarly segregated into a wide range of fiber strengths. Plants that were apparently GUS heterozygotes 7, 8, 34, and 73, also produced a wide range in fiber strength (strength data in Table 1 is only for the GUS+ plants). The data from M₁₆ plant #73 GUS- plants (n=262, mean=20.0 +1.1 g/tex, range 17.2-23.3 g/tex) indicates that none produced a fiber strength near that of the high strength (>25 g/tex) GUS+ plants (suggesting that the GUS gene and

References

Deussen, H. (1992): Improved cotton fiber properties - the textile industry's key to success in global competition. In: Cotton Fiber Cellulose: Structure, Function and Utilization Conference.: C.R. Benedict and G.M. Jividen (Ed.) Natl. Cotton Council, Memphis, TN. Pp. 43-63.

strength gene have not been disassociated through recombination), and that the plant-to-plant standard deviation was of a similar small magnitude as that observed in DP 50. The R₄ and R₅ data from M₁₆ populations suggest that it may not be possible to extract a true breeding genotype that consistently expresses increased strength.

Instrument measurement variation may be insufficiently large to explain strength segregation among GUS+ plants. Some of the fiber strength variation among these plants could reflect where the boll samples were taken from the plants (Lewis, 1996). In a detailed study of fiber strength variation as affected by fruiting zone within DP 50, Lewis (1996) found that strength as measured by HVI varied by up to 1.6 g/tex but that in a higher strength cultivar, strength varied as much as six g/tex. Experiments have not been conducted yet with a high strength transformed plant similar to Lewis (1996), thus we are not aware of how much variation exists within a transformed plant for fiber strength.

If a true breeding line cannot be isolated from the descendants of the original DP 50 transformant, the goal may be reached by observing transgene behaviour in different genetic backgrounds. The impact of genetic background on the efficacy of genetic engineering has been demonstrated (Jenkins *et al.*, 1997; Sachs *et al.*, 1998), rendering the colculsio based on these M₁₆ data only preliminary. Sufficient numbers of populations containing GUS and the proprietary gene homozygotes have to be sampled to determine segregation for strength. Two F₁ populations of crosses with plant #34 and one F₁ population involving plant #48 gave data (high mean strength and low plant-to-plant standard deviation; data not shown) suggesting that fiber strength expression might be more stable in a different genetic background than the original transformant. F₂ progeny rows from these F₁ plants are being evaluated in the field.

Although no commercial product is imminent from this research, we are continuing breeding efforts to isolate a germplasm with stable expression of increased strength.

Acknowledgement

We thank Debbie Cottingham, Oliver Heath, and Ronda Mathews for excellent technical assistance.

Jefferson, R.A., T.A. Kavanagh and M.W. Bevan. (1987): *GUS* fusions: B-Glucuronidase as a sensitive and versatile gene fusion marker in higher plants. *EMBO J.* 13:3901-3907.

Jenkins, J.N., J.C. McCarty, Jr., R.E. Buehler, J. Kiser, C. Williams and T. Wofford. (1997): Resistance of cotton with delta-endotoxin genes from *Bacillus*

- thuringiensis* var. *kurstaki* on selected lepidopteran insects. *Agron. J.* 89:768-780.
- John, M.E. (1996): Metabolic pathway engineering in cotton: Biosynthesis of polyester fiber. In: Proc. Belt. Cotton Res. Conf. P. Dugger and D.A. Richter (Ed.). Natl. Cotton Council, Memphis, TN. Pp. 167-9
- Lege, K.E. (1995): South Carolina Cotton Growers Guide. South Carolina Agric. & Forestry Exp. Stn. Circ. 589.
- Lege, K.E. (1995): South Carolina Cotton Growers Guide. South Carolina Agric. & Forestry Exp. Stn. Circ. 589.
- Lewis, H.L. (1996): Variation in cotton fiber quality. In: Proc. 9th Engineered Fiber Selection System Conf. C.H. Chewning (Ed.). Cotton Inc., Raleigh, NC. Pp. 29-33
- May, O.L. (1998): Genetic variation in fiber quality. In: Cotton Fibers. A.S. Basra (Ed.) Food Products Press, Binghamton, NY (In press).
- McCabe, D.E. and B.J. Martinell. (1993): Transformation of elite cotton cultivars via particle bombardment of meristems. *Biotech.* 11:596-598.
- Sachs, E.S., J.H. Benedict, D.M. Stelly, J.F. Taylor, D.W. Altman, S.A. Berberich and S.K. Davis. (1998): Expression and segregation of genes encoding CryIA insecticidal proteins in cotton. *Crop Sci.* 38:1-11.

Table 1. GUS-Phenotype and fiber strength (by Stelometer measurement) of transformed DP 50 plants evaluated in field trials near Florence, SC.

Population	Plant # ^a	GUS phenotype	1996 T ₁ g/tex	1997 GUS Segregation		GUS+ Mean	1997 T ₁ Segregation		Standard ^b Deviation
				+	-		Range g/tex		
M16	1	+	29.2	15	0	22.5	17.9	27.1	3.3
	5	+	24.3	-----		---	-----	---	
	6	+	31.4	2	0	23.5	20.9	26.1	---
	7	+	26.0	205	120	21.1	15.2	28.2	1.6
	8	+	29.9	304	326	----	-----	---	
	11	+	31.4	2	0	18.8	17.5	20.1	---
	12	+	29.8	11	0	20.6	16.2	26.9	3.5
	13	+	26.6	-----		---	-----	---	
	21	+	31.7	21	1	23.6	18.0	30.4	3.1
	23	+	25.7	-----		---	-----	---	
	31	+	30.4	56	2 (OP)	----	-----	---	
	34	+	30.1	276	302	25.3	18.1	30.0	1.6
	41	+	31.0	7	0	25.0	19.4	28.9	3.4
	44	+	29.8	2	0	----	-----	---	
	47	-	23.2	-----		----	-----	---	
	48	+	29.8	131	126	----	-----	---	
	49	-	21.6	-----		----	-----	---	
	52	+	23.2	-----		----	-----	---	
	53	+	24.7	-----		----	-----	---	
	54	+	23.8	-----		----	-----	---	
	56	+	23.8	-----		----	-----	---	
	63	+	24.4	-----		----	-----	---	
	64	-	23.4	-----		----	-----	---	
67	+	24.0	-----		----	-----	---		
72	+	27.2	165	213	----	-----	---		
73	+	31.4	207	269	25.5	18.6	29.4	1.5	
		SD	3.3						

1996 DP 50 average T₁=17.1 ±1.1; 1997 average 19.2 ±1.1.

^a Some 1996 plants failed to produce fiber, thus there exists gaps in sequence of plant numbers. Missing 1997 data reflects plants not advanced to a progeny row.

^b Standard deviation in 1997 fiber strength is indicative of amount of plant-to-plant variation in strength within a progeny row.